Cromalent Orange S2

Chemical Nature: Monoazo Chromium complex

Physical Properties

Form	ge I.	
Solubility in water Inso Specific gravity (water=1) 1.20 Light Fastness 1-8 Blue Scale comparison 6-7 Heat Fastness 10 min. 180°C (1-5 scale) 5))	
Specific gravity (water=1) 1.20 Light Fastness 1-8 Blue Scale comparison 6-7 Heat Fastness 10 min. 180°C (1-5 scale) 5)	
Light Fastness 1-8 Blue Scale comparison 6-7 Heat Fastness 10 min. 180°C (1-5 scale) 5		
1-8 Blue Scale comparison6-7Heat Fastness10 min. 180°C (1-5 scale)5		
Heat Fastness 10 min. 180°C (1-5 scale) 5		
10 min. 180°C (1-5 scale) 5		
Chemical Fastness		
Acid (1-5 scale) 5		
Alkali (1-5 scale) 5		
Table of solubilities		
Methanol 170)	
Ethanol 100)	
Isopropanol 190)	
Isobutanol 140)	
n-Butanol 310)	
Ethylacetate 100)	
Toluene -		
Xylene -		
MEK 500)	
MIBK 380)	
Ethyl Cellosolve 490)	
Cyclo-Hexanone 500)	
PM (Propylene Glycol Methyl Ether) 360)	
DPM (Dipropylene Glycol Methyl Ether) 400)	
Acetone 140)	

APPLICATIONS	
Wood Stains	Δ
Hot stamping	٨
1 0	Α
Natural or sinthetic leather coatings	A
Soles of shoes coatings	Α
Transparent coating for aluminium foil	Α
Transparent coating for metallized film	Α
Solvent based flexografic inks	Α
Ink-jet inks	Α

1		
2,5%	RECIPE FOR ILLUSTRATION	1%
9	NC resine	9
21	Ethylacetate	21
10	Metoxipropanol	10
27,5	MEK	29
30	Ethanol	30
2,5	Dye	1
100		100

Legenda: A= suitable, B= applicable previous tests, C= unsuitable. Illustrations have been obtained by a 24 micron coater.

Fastness methods: Light: ISO blue scale (1-8) as comparison standard. / Heat: Automatic constant temperature dryer at 180°C for 10 minutes. / Acid: Immerse in 1% H2SO solution for 24 h. / Alkali: Immerse in 1% NaOH solution for 24h.

Solubilities: Figures given in the table represent the amount of dye in grams which may be dissolved in a litre of the indicated solvent. Test is conducted for each solvent by making a sequence of drawdowns with a 30 micron coater on aluminium foil at increasing values of solved dye. Drawdown must be glossy ans trasparent, with no opacity, while no bottom must be present in the container.

Other informations: The above informations are based on our actual knowledge and on the results of the tests in our lab, but they are given without guarantee. Tests before the industrial use of the product are recommended.