



THE CARBON NANOTUBE SPECIALIST

NANO-ENGINEER YOUR FUTURE

PREGCYL

Ref: PREGCYL™ NC R2HM-01 –27 February 2009 - V01

PREGCYL™ NC R2HM-01 Product Data - Pre-impregnated UD/Fabric carbon fibres

General information

Description

PREGCYL™ NC R2HM-01 is a Pre-impregnated material based on our EPOCYL NC R2HM01 formulated epoxy based resin system modified with our own Carbon Nanotubes (CNT) and specifically developed to enhance the mechanical properties of the final composite parts.

Applications: High performance composite parts

- Automotive (bumpers and other structural parts)
- Marine, especially sailing boats (structural outer shell in carbon fiber composite, masts and other generic structural parts)
- Industrial parts (rollers, doctor-blades and wind-mill blades)
- Sporting equipments (bike frames, hockey sticks, tennis rackets, skis and golf shafts)
- Aerospace (structural parts and interiors)

Advantages

- High toughness (over 1200j/m² in some configurations)
- Low CTE
- 120° Tg
- Easy and ready to use
- Higher uniformity of temperature during curing (avoids hot-spots)

Nanocyl S.A.

Rue de l'Essor 4 Tel +32 71 750 380
B-5060 Sambreville Fax +32 71 750 390
BELGIUM sales@nanocyl.com

US contact

info-us@nanocyl.com

www.nanocyl.com

Curing cycles suggested

Curing	Gel time	Post Curing	Tg (measured by DSC)
5h at 100°C	60 min		About 120°C
1h at 120°C	15 min		About 120°C
2h at 120°C	15 min		About 120°C
1h at 130°C	8 min		About 120°C
30' at 140°C	5 min		About 120°C
1h at 120°C	15 min	2h at 140°C	About 125°C

Heating ramp suggested: 3-4°C/min. Cooling ramp suggested: 2-3°C/min.

Shorter curing cycles are possible but specific testing may be needed to validate.

Examples of fibers and fabrics available

- 200 g/m2 plain and twill 2/2 weave, 3K; 45% resin content
- 370 g/m2 Harness 5 weave, 6K; 45% resin content
- 400 g/m2 twill 2/2 weave 12K; 45% resin content
- 600 g/m2 twill 2/2 weave 12K; 45% resin content
- 150g/m² UD; 37% resin content
- 100g/m² UD; 37% resin content
-

Properties of the cured and fiber reinforced composite

Unless otherwise stated the values given are for pressed laminates comprising 8 layers of unidirectional (UD) carbon fibers high tenacity (Tenax 12K HTS 5631) of 230 g/m². Fiber volume fraction: 58-60%.

Curing cycle: 1h at 120°C + 2h at 140°C combined with low pressure.

Fracture Toughness (G1C) – ASTM 5528	1200 J/m²
Compression Strength – ASTM D3410	553 Mpa
Coefficient of thermal expansion (CTE) – thermo mechanical analysis	2,97 x 10⁻⁵ / °K
Electrical Conductivity	2,5·10⁻⁶ [S/m] = 4·10³ [Ω·cm]

Important

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purposes required.

For technical assistance, sales or further information, please contact us :

Nanocyl S.A.

Rue de l'Essor 4 Tel +32 71 750 380
B-5060 Sambreville Fax +32 71 750 390
BELGIUM sales@nanocyl.com

US contact

info-us@nanocyl.com