

INTRODUCTION

Indorez™ C9 Hydrocarbon Resin, H-120-14 resin is thermo-polymerized C9 aromatic hydrocarbon resins which has following key characteristics.

- Lower odor and no PAHs contains
- Improve tack, bond strength, and down the cost in adhesive.

SPECIFICATIONS

Tests	Unit	Specifications
Appearance	-	Brownish Granule
Color	Gardner in 50% toluene	Max 14
Softening point	°C	111-120
Acid value	KOH mg/g	Max 0.05
Ash content	wt.%	Max 0.05
Bromine Value	Br cg/g	Max 85
Additional Tests*		
Melt Viscosity at 200 °C	CPS	100 ± 20
Flash Point	°C	Min 275
Specific Gravity 20/20 °C		1.07

* Tests for reference will not be reported on COA.

APPLICATION

- Contact Adhesive
- Rubber additive
- Solvent Based Adhesives
- Paints

PACKAGING

25 Kgs PP bags with HDPE liner

Reference No: ON/H-00040	Issue Date: February 20, 2015	Prepared By: Dnyaneshwar Shekare	Date: 14/05/2015
Revision No: 01	Revision Date: May 14, 2015	Approved By: Deepali Nikam	Date: 14/05/2015

Disclaimer: The information above is believed to be accurate and represents the best information currently available to us. However, we make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and we assume no liability resulting from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no way shall Onward Chemicals Pvt Ltd be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if Onward Chemicals Pvt Ltd has been advised of the possibility of such damages.



ONWARD CHEMICALS PVT. LTD

Head office

10-11, Creative Estate
 N.M. Joshi Marg
 Lower Parel (E)
 Mumbai 400 011, INDIA

T: +91-22- 4054 6474
 F: +91-22- 4054 6400
 W: www.onwardchem.com
 E: info@onwardchem.com

Delhi Office

T: +91-129-2510748
 F: +91-129-2510530
 W: www.onwardchem.com
 E: delhi@onwardchem.com

Chennai Office

T: +91-44-26801175
 F: +91-44-26801175
 W: www.onwardchem.com
 E: chennai@onwardchem.com